



Quality Management System certified ISO 9001: 2015 by Intertek

Prodotto da: TIXE srl - 15060 CAPRIATA D'ORBA (AL) ITALY
Via C. Ferrari, 49 (Frazione Pratalborato) - T. +39 0143 46397
www.tixepaint.com - mail@tixepaint.com - P.IVA 01779900992
MADE IN ITALY - UN 1263 PAINT



Famiglia: EDILIZIA



Prodotto: PORDOI

DESCRIZIONE

Pittura murale per interni ad elevata traspirabilità ed opacità, dotata di buon punto di bianco e potere coprente.

CARATTERISTICHE PRINCIPALI

Elevatissima traspirabilità
Buon punto di bianco
Buona copertura
Ottima applicabilità

IMPIEGO

Pittura murale per interni dotata di buon punto di bianco, potere coprente e opacità, formulata nell'intento di privilegiare al massimo la traspirabilità di ambienti a media umidità come bagni, cucine, cantine. Pur essendo applicabile a pennello e rullo è particolarmente indicata per il trattamento a spruzzo di locali industriali. Idonea anche per pareti di locali nei quali occorra fare soviente manutenzione. Utilizzata per mascherare imperfezioni del muro, grazie all'ottima opacità.

APPLICAZIONE

La superficie da pitturare con PORDOI deve essere preparata con trattamento idoneo, e precisamente:

SU SUPPORTI NUOVI (STUCCO o MALTA): per un miglior ancoraggio e per una maggiore durata nel tempo, la superficie deve essere esente da unto o spolvero. Applicare a pennello una mano di isolante o fissativo. Dopo minimo 4 ore, applicare due mani di PORDOI.

SU SUPPORTI GIA' Pitturati:

con idropitture lavabili: stuccare e carteggiare se necessario; pulire il muro con spugna umida ed applicare una mano a pennello di isolante o fissativo solo sulle stuccature. Dopo minimo 4 ore applicare due mani di PORDOI.

con tempere, pitture a calce o pitture sfarinanti: stuccare e carteggiare se necessario; pulire il muro con spugna umida, applicare una mano a pennello di fissativo o isolante su tutta la superficie. Dopo minimo 4 ore applicare due mani di PORDOI.

Applicazioni consigliate: a pennello, rullo, airless, spruzzo.

Condizioni dell'ambiente e del supporto:

Il supporto deve essere asciutto, privo di polvere, di unto e di ogni altra sostanza inquinante

Temperatura dell'ambiente: min. 10°C / max 35°C

Umidità relativa dell'ambiente: < 75%

Temperatura del supporto: min. 10°C / max 35°C

DILUIZIONE

Il prodotto è da diluire con acqua: le quantità sono relative all'attrezzo impiegato e al tipo di finitura desiderata:
pennello fino a 40% in volume (1-2 mani),
pennello finitura laccata fino a 60% in volume (3-4 mani),
rullo 30% in volume (1-2 mani).

Si raccomanda una accurata mescolazione del prodotto prima dell'applicazione, in modo tale da garantire la costante omogeneità del prodotto.



Quality Management System certified ISO 9001: 2015 by Intertek

Prodotto da: TIXE srl - 15080 CAPRIATA D'ORBA (AL) ITALY
Via C. Ferrari, 49 (Frazione Pratalavoro) - T. +39 0143 46392
www.tixepaint.com - mail@tixepaint.com - P.IVA 01779800992
MADE IN ITALY - UN 1263 PAINT



STOCCAGGIO

Conservare il barattolo ben chiuso, al riparo dal gelo e da fonti di calore.

CARATTERISTICHE FISICHE (a 20°C +1°C e 50% - 60% U.R.)

Peso specifico	1,60 ± 0,02 Kg/l
Resa (*)	4-5 m ² /l per 2 mani, 8-10 m ² /l per mano singola
Viscosità	70000-80000 cP Brookfield vel.2
Essiccazione	1 ora secco al tatto
Vita di stoccaggio	6 ore per la ricopertura Almeno 36 mesi

(*) La resa dipende dalla natura e dalla porosità della superficie.

PRECAUZIONI

Oltre alle segnalazioni di rischio e precauzione che regolano PORDOI nella forma di produzione e che sono riportate sul contenitore, si consiglia, prima di effettuare l'applicazione del prodotto, di consultare la relativa SCHEDA DI SICUREZZA. E' comunque buona norma impiegare guanti ed occhiali di protezione, ed effettuare l'applicazione in ambiente ben aerato.



Quality Management System certified ISO 9001: 2015 by Intertek
Prodotto da: TIXE srl - 15080 CAPRIATA D'ORBA (AL) ITALY
Via C. Ferrari, 49 (Frazione Pinalborato) - T. +39 0143 46392
www.tixepaint.com - mail@tixepaint.com - P.IVA 01779800992
MADE IN ITALY - UNI 1263 PAINT



Family: BUILDING



Product: PORDOI

DESCRIPTION

Wall paint for interiors with high breathability and opacity, with good whiteness and covering power.

MAIN FEATURES

Very high breathability
Good white point
Good coverage
Excellent applicability

USE

Interior wall paint with a good whiteness, hiding power and opacity, formulated with the intention of giving maximum priority to the breathability of medium humidity environments such as bathrooms, kitchens, cellars. Although applicable by brush and roller, it is particularly suitable for the spray treatment of industrial premises. Also suitable for walls in rooms where frequent maintenance is required. Used to mask wall imperfections, thanks to the excellent opacity.

APPLICATION

The surface to be painted with PORDOI must be prepared with a suitable treatment, namely:

ON NEW SUBSTRATES (STUCCO or MORTAR): for better anchoring and longer life, the surface must be free from grease or dust. Apply a coat of sealer or fixative with a brush. After at least 4 hours, apply two coats of PORDOI.

ON ALREADY PAINTED SUPPORTS:

with washable water-based paints: fill and sand if necessary; clean the wall with a damp sponge and apply a brush coat of insulation or fixative only on the grouting. After at least 4 hours, apply two coats of PORDOI.

with tempera, lime paints or chalking paints: fill and sand if necessary; clean the wall with a damp sponge, apply a brush coat of fixative or insulator over the entire surface. After at least 4 hours, apply two coats of PORDOI.

Recommended applications: by brush, roller, airless, spray.

Conditions of the environment and support:

The substrate must be dry, free from dust, grease and any other polluting substance

Ambient temperature: min. 10 ° C / max 35 ° C

Relative humidity of the environment: <75%

Substrate temperature: min. 10 ° C / max 35 ° C

DILUTION

The product is to be diluted with water: the quantities are related to the tool used and the type of finish desired:

brush up to 40% by volume (1-2 coats),

lacquered finish brush up to 60% by volume (3-4 coats),

roller 30% by volume (1-2 coats).

Careful mixing of the product is recommended before application, in order to ensure the constant homogeneity of the product.

STORAGE

Keep the jar tightly closed, away from frost and heat sources.



Quality Management System certified ISO 9001: 2015 by Intertek

Prodotto da: TIXE srl - 15080 CAPRIATA D'ORBA (AL) ITALY

Via C. Ferrari, 49 (Frazione Piattofiorato) - T. +39 0143 46392

www.tixepaint.com - mail@tixepaint.com - P.IVA 01779800992

MADE IN ITALY - UN 1263 PAINT



PHYSICAL CHARACTERISTICS (at 20°C +1°C and 50% - 60% R.H.)

Specific weight	1.60 - 0.02 Kg / l
Coverage (*)	4-5 m2 / l for 2 coats, 8-10 m2 / l for single coat
Viscosity	70000-80000 cP Brookfield vel. 2
Drying	1 hour dry to the touch
	6 hours for recoating
Storage life	At least 36 months

(*) The yield depends on the nature and porosity of the surface.

PRECAUTIONS

In addition to the risk and precautionary warnings that regulate PORDOI in the form of production and which are shown on the container, it is advisable, before applying the product, to consult the relevant SAFETY DATA SHEET.

In any case, it is good practice to use protective gloves and goggles, and to apply in a well-ventilated environment