



Quality Management System certified ISO 9001: 2015 by Intertek

Prodotto da: TIXE srl - 15060 CAPRIATA D'ORBA (AL) ITALY
Via C. Ferrari, 49 (Frazione Pratalborato) - T. +39 0143 46307
www.tixepaint.com - mail@tixepaint.com - P.IVA 01779800992
MADE IN ITALY - UM 1263 PAINT



Famiglia: DECORATIVI



Prodotto: PERLATIX

DESCRIZIONE

Finitura decorativa ad effetto madreperlato di facile applicazione, ideale per rinvigorire le colorazioni già presenti sulle proprie pareti.

CARATTERISTICHE PRINCIPALI

- Effetto decorativo madreperlato liscio o sabbiato
- Effetto cromatico interferenziale
- Buona trasparenza
- Ottima adesione
- Ottima lavabilità
- Facilità di impiego

IMPIEGO

Il prodotto permette di impreziosire la superficie trattata con un eccezionale effetto madreperlato, ottenendo così ambienti dall'aspetto moderno e con effetti cromatici che variano in base all'inclinazione della luce. Grazie alla particolare trasparenza, PERLATIX permette la visibilità della colorazione murale sottostante prescelta, che risulterà arricchita dall'effetto madreperla. Disponibile in versione tradizionale liscia e sofisticata sabbiata, PERLATIX aggiunge alla classica colorazione trasparente madreperla, anche quelle trasparenti oro, rame e argento. PERLATIX è dotato di ottima adesione e lavabilità.

APPLICAZIONE

Sul sito web www.tixepaint.com è possibile consultare il tutorial dimostrativo.

La superficie da verniciare con PERLATIX deve essere preparata con trattamento idoneo, e precisamente:

SU SUPPORTI NUOVI (STUCCO o MALTA): per un miglior ancoraggio e per una maggiore durata nel tempo, la superficie deve essere esente da unto o spolvero. Applicare a pennello una mano di fissativo e idropittura dalla colorazione prescelta. Dopo minimo 4 ore, applicare PERLATIX in versione liscia o sabbiata. Il metodo di applicazione varia in base alla tipologia di finitura prescelta e di movimento che si vuole conferire: obliqua, verticale, tramato, ad incrociare, ondulato, etc.

SU SUPPORTI GIA' Pitturati:

con idropitture in fase di distacco o logore, stuccare e carteggiare se necessario; pulire il muro con spugna umida ed applicare una mano a pennello di isolante o fissativo solo sulle stuccature. Applicare una idropittura dalla tinta prescelta. Dopo minimo 4 ore applicare PERLATIX in versione liscia o sabbiata. Il metodo di applicazione varia in base alla tipologia di finitura prescelta e di movimento che si vuole conferire: obliqua, verticale, tramato, ad incrociare, ondulato, etc.

con idropitture in buono stato e da mantenere come fondo, applicare PERLATIX in versione liscia o sabbiata. Il metodo di applicazione varia in base alla tipologia di finitura prescelta e di movimento che si vuole conferire: obliqua, verticale, tramato, ad incrociare, ondulato, etc.

Applicazioni consigliate:

Spalter, pennello, rullo.



Quality Management System certified ISO 9001:2015 by Intertek

Prodotto da: **TIXE** srl - 15060 CAPRIATA D'ORBA (AL) ITALY
Via C. Ferrati, 49 (Frazione Pratalborato) - T. +39 0143 46387
www.tixepaint.com - mail@tixepaint.com - P.IVA 01779800992
MADE IN ITALY - UM 1263 PAINT



Condizioni dell'ambiente e del supporto:

Il supporto deve essere asciutto, privo di polvere, di unto e di ogni altra sostanza inquinante

Temperatura dell'ambiente: min. 10°C / max 35°C

Umidità relativa dell'ambiente: < 75%

Temperatura del supporto: min. 10°C / max 35°C

DILUIZIONE

Il prodotto è da impiegare tal quale, oppure discrezionalmente diluibile con acqua. Si raccomanda una accurata mescolazione del prodotto prima dell'applicazione, in modo tale da garantire la costante omogeneità del prodotto.

STOCCAGGIO

In ambiente fresco e ben ventilato.

Conservare il barattolo ben chiuso, capovolto e al riparo dal gelo e da fonti di calore.

CARATTERISTICHE FISICHE (a 20 °C e 50% - 60% U.R.)

Peso specifico	1.0 ± 0.15 Kg./l BASE LISCIA
	1.1 ± 0.15 Kg./l BASE SABBIATA

Resa (*)	12 m ² /l per mano
----------	-------------------------------

Viscosità	30000 - 40000 cP Brookfield vel.2
-----------	-----------------------------------

Essiccazione	5 ore fuori impronta
	18 ore in profondità

Vita di stoccaggio	Almeno 36 mesi
--------------------	----------------

(*) La resa dipende dalla natura e dalla porosità della superficie.

Il prodotto è disponibile nelle versioni liscia e sabbiata, rispettivamente nelle cromaticità madreperla, oro, argento, rame, rainbow.

PRECAUZIONI

Oltre alle segnalazioni di rischio e precauzione che regolano PERLATIX nella forma di produzione e che sono riportate sul contenitore, si consiglia, prima di effettuare l'applicazione del prodotto, di consultare la relativa SCHEDA DI SICUREZZA. È comunque buona norma impiegare guanti ed occhiali di protezione, ed effettuare l'applicazione in ambiente ben aerato.



Quality Management System certified ISO 9001: 2015 by Intertek

Prodotto da: TIXE srl - 15060 CAPRIATA D'ORBA (AL) ITALY
Via C. Ferrari, 49 (Frazione Pratalborato) - T. +39 0143 46397
www.tixepaint.com - mail@tixepaint.com - P.IVA 01779800992
MADE IN ITALY - UM 1263 PAINT



Family: DECORATIVE PAINT



Product: PERLATIX

DESCRIPTION

Decorative finish with a mother-of-pearl effect, easy to apply and ideal for reviving the colors already present in your walls.

MAIN FEATURES

- Smooth or sanded mother-of-pearl decorative effect
- Interference color effect
- Good transparency
- Excellent adhesion
- Excellent washability
- Ease of use

USE

The product allows to embellish the treated surface with an exceptional pearly effect, thus obtaining environments with a modern look and with chromatic effects that vary according to the inclination of light. Thanks to the particular transparency, PERLATIX allows the visibility of the chosen underlying mural coloring, which will be enriched by the mother-of-pearl effect. Available in the traditional smooth and sophisticated sandblasted version, PERLATIX adds to the classic transparent mother-of-pearl color, even the transparent gold, copper and silver. PERLATIX has excellent adhesion and washability.

APPLICATION

On the website www.tixepaint.com it is possible to consult the demonstration tutorial.

The surface to be painted with PERLATIX must be prepared with a suitable treatment, namely:

ON NEW SUPPORTS (STUCCO or MALTA): for a better anchorage and a longer life, the surface must be free of grease or dust. Apply a coat of fixative and water-based paint with a selected paint. After at least 4 hours, apply PERLATIX in a smooth or sanded version. The method of application varies depending on the type of finish chosen and the movement that you want to give: oblique, vertical, textured, to cross, wavy, etc.

ON ALREADY PAINTED SUPPORTS:

with water-based paints in the phase of separation or wear, fill and sand if necessary; clean the wall with a damp sponge and apply one coat with an insulating brush or fixative only on stuccoing. Apply a water paint with the chosen color. After at least 4 hours, apply PERLATIX in a smooth or sanded version. The method of application varies depending on the type of finish chosen and the movement that you want to give: oblique, vertical, textured, to cross, wavy, etc.

with water-based paints in good condition and to be maintained as a base, apply PERLATIX in a smooth or sanded version. The method of application varies depending on the type of finish chosen and the movement that you want to give: oblique, vertical, textured, to cross, wavy, etc.

Recommended applications: Spalter, brush, roller.

Environmental and support conditions:

The substrate must be dry, free of dust, grease and any other pollutant

Room temperature: min. 10 ° C / max 35 ° C



Quality Management System certified ISO 9001:2015 by Interlev

Prodotto da: TIXE srl - 15060 CAPRIATA D'ORBA (AL) ITALY
Via C. Ferrari, 49 (Frazione Pratalborato) - T. +39 0143 46387
www.tixepaint.com - [mail@tixepaint.com](mailto:tixepaint.com) - P.IVA 01779800992
MADE IN ITALY - SIN 1265 PAINT



Relative humidity of the environment: <75%
Support temperature: min. 10 ° C / max 35 ° C

DILUTION

The product is to be used as it is, or it can be discreetly diluted with water. It is recommended to carefully mix the product before application, in order to guarantee constant product homogeneity.

STORAGE

In a cool and well-ventilated environment.

Keep the tin tightly closed, overturned and protected from frost and heat sources.

PHYSICAL CHARACTERISTICS (at 20 ° C and 50% - 60% U.R.)

PHYSICAL CHARACTERISTICS (at 20 °C and 50% RH):
Specific weight 1.0 – 0.15 Kg/l **BASE LISCIA**
1.1 – 0.15 Kg/l SANDBLASTED BASE

Yield (*) 12 m² / l per coat

Viscosity 30000 -40000 cP Brookfield vel.2

Drying 5 hours off impression
18 hours in depth

Storage life At least 36 months

(*) The yield depends on the nature and porosity of the surface.

The product is available in smooth and sanded versions, respectively in mother-of-pearl, gold, silver, copper and rainbow chromaticity.

PREFCAUTIONS

PRECAUTIONS
In addition to the risk and precautionary reports that regulate PERLATIX in the form of production and which are shown on the container, it is recommended, before applying the product, to consult the relevant SAFETY DATA SHEET. However, it is good practice to use protective gloves and goggles, and to apply it in a well-ventilated area.